

GENERAL MASONRY MORTAR

*PREMIUM PRODUCT
OF THAILAND*



Clay Bricks



Concrete Blocks



GENERAL MASONRY MORTAR

Product Information

- For laying clay bricks and concrete blocks

Product Features

- Easier laying and aligning from increased viscosity of mixture from water retention agent
- Enhanced bonding and wall strength from added adhesive agent

Special Properties

- Suitable for all types of clay bricks and concrete blocks
- Reduced laying time

Application Method

- Mix 1 bag of cement with 7-9 liters of clean water
- If mixing with trowel, do not mix more than 5 kilograms per batch
- Ensure cement is well blended before use

Application area

- 1.0-1.5 m² for 1-2 centimeters thickness with clay bricks
 - 2.0-2.8 m² for 1-2 centimeters thickness with concrete blocks
- *Information supplied from laboratory test

Recommendations

- Use within 2 hours of mixing
- Do not add water after mortar has begun to set
- Install wire rod every 50 centimeters to increase wall strength
- Do not add other materials such as sand to avoid disproportion of mixture
- Spray with water 2-3 days after laying

TECHNICAL DATA

Product Identity

Type : Powder
 Color : Grey
 Storage : Keep in dry conditions and avoid moisture
 Shelf Life : up to 2 months
 Packaging : 50 kilograms per bag

Application Data

Application : For laying clay bricks or concrete blocks
 Layer Thickness : 1-3 centimeters
 Mixing Water : 7-9 liters per bag
 Temperature Range : 20-40°C
 Application Humidity : minimum 50%
 Pot Life (25°C) : 120 minutes

Test Data

Property (Method)	Result
Wet Property	
pH of mix (pH meter)	~11
Air Content (ASTM C185)	5-10%
Water Retention (TIS 598)	75-93%
Time of Setting (ASTM C807)	60-130 minutes
Dry Property	
Compressive Strength (ASTM C109)	
28 days	> 5.0 MPa
Bonding Strength (ASTM C952)	
7 days	> 0.1 N/mm ²
28 days	> 0.1 N/mm ²

Additional Suggestions



Recommendation for Cement Bag Handling : To lift cement bag, kneel down with a straight back, securely hold product with hands, then use the power from your legs to lift product. Women, children, the elderly and those with health conditions or disabilities should not move cement bags without assisting equipment.



Cautions • Do not use product with lightweight blocks • Suitable temperature for use is between 20°C - 40°C • Avoid using product in direct sunlight or in windy conditions
Safety Precautions • Avoid breathing in cement and avoid direct contact with concrete. Use of protective masks, protective goggles, and waterproof clothing, shoes and gloves is advised.
 • Avoid direct contact with concrete. Use of protective goggles, waterproof clothing, shoes and gloves is advised. • Avoid inhaling concrete dust • If concrete dust comes in contact with eyes or mouth, wash thoroughly with clean water and seek medical advice immediately. • If concrete dust comes in contact with skin, wash thoroughly with clean water. If irritations occur such as itching, rashes or burning sensation in area of contact with concrete dust, seek medical advice immediately. • Clothing stained with concrete dust should be washed thoroughly before reuse • Do not reuse packaging material as a container for food or drinks • Keep away from children

For additional inquiries about use of product, application method, material safety data sheets (MSDS), or other information, please contact SCG Contact Center +662-586-2222 or www.scg-trading.com



SCG International Corporation Co., Ltd.
 1 Siam Cement Road Bangsue,
 Bangkok 10800, Thailand
 Tel. +662-586-2222

Agent's stamp